PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5:		(11) International Publication Number:	WO 92/13491
A61B 17/064	A1	(43) International Publication Date:	20 August 1992 (20.08.92)
(21) International Application Number: PCT/US9 (22) International Filing Date: 8 January 1992 (patent), CA, CH (European tent), DK (European patent), (European patent), GB (European patent)	patent), DE (European pa- ES (European patent), FR ropean patent), GR (Euro-
(30) Priority data: 653,353 6 February 1991 (06.02.91) t	pean patent), IT (European patent), MC (European patent). SE (European patent).	patent). JP. LU (European
(71) Applicant: MINNESOTA MINING AND MAN TURING COMPANY [US/US]; 3 M Center, fice Box 33427, Saint Paul, MN 55133-3427 (US	Post O	Published With international search repo	rt.
(72) Inventors: VIDAL, Claude; REDMOND, Russ P.O. Box 33427, Saint Paul, MN 55133-3427 (U	ell, J. S).	;	
(74) Agents: HOHENSHELL, Jeffrey, J. et al.; P.O. Bo. Saint Paul, MN 55133-3427 (US).	x 3342		
			·

(54) Title: IMPROVED SURGICAL HARDWARE WITH BACTERIOSTATIC SILVER COATING, AND METHOD OF USING SAME



(57) Abstract

A staple, wire suture, clip, or other item of surgical hardware is disclosed which can be used to close a wound, made from a high strength metal to have a low profile design to minimize interference and disturbance of the wound, and having a bacteriostatic silver coating to reduce the risk of wound infection from the hardware. A method of closing surgical wounds with reduced risk of infection is also disclosed, the method includes the steps of closing the wound with a staple, wire suture, clip, or other item of surgical hardware made from a high strength metal that has a silver coating.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

ΤA	Austria	FI	l-inland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Burbados	GA	Gabon	MR	Mauritania
BE	Belgium	CB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL.	Netherlands
BC	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	ΙE	Ireland	RO	Romania
CA	Canada	IТ	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CC	Congo	KP	Democratic People's Republic	SE	Sweden
CH	Switzerland		of Korea	SN	Senegal
CI	('ôte d'Ivaire	KR	Republic of Korea	SU	Soviet Union
CM	Cameroon	LI	l icchtenstein	TD	Chad
CS	Czechoslovakia	LK	Sri Lanka	TG	Togo
DE	Ciermany	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		
FS	Smain	MG	Madagascar		

WO 92/13491 PCT/US92/00209

IMPROVED SURGICAL HARDWARE WITH BACTERIOSTATIC SILVER COATING, AND METHOD OF USING SAME

5 BACKGROUND OF THE INVENTION

10

15

20

25

30

This invention relates to surgical hardware of the type used to close wounds, and to an improved method of closing wounds using such hardware.

Various items of metal hardware have been developed to assist in closing wounds. At one time such hardware was made from solid silver. However, because of silver's high ductility and relatively low strength, silver hardware had to be made very coarse to have adequate mechanical properties. For many applications solid silver hardware was objectionably coarse. High strength metals such as stainless steel and titanium, permit more slender, clinically desirable hardware designs, and have for decades been the state of the art materials for surgical hardware.

Wound infection is always a serious concern because of its system-wide effect and retardation of normal wound healing, but when surgical hardware is required and used there are additional potential complications from wound infection including dehiscence or splitting of the wound, leakage from the wound, and formation of adhesions. While conventional steel and titanium hardware can be sterilized, it does not appear to have significant bacteriostatic effect, and may actually promote infection compared with other materials. Nevertheless, because these high strength metals permit the manufacture of such small, high strength hardware, these metals are still widely used.

SUMMARY OF THE INVENTION

35 The present invention provides an improved item of surgical hardware that provides the strength and compact size of a high strength metal such as stainless steel or titanium, and bacteriostatic properties to reduce the risk of wound infection. This hardware allows wounds to be

'

WO 92/13491

5

10

15

20

25

30

neatly and effectively closed, and provides some bacteriostatic action that reduces the risk of many of the complications encountered in the use of surgical hardware.

The invention relates to a staple, wire suture, clip, or other item of surgical hardware used in closing wounds. Generally, the surgical hardware constructed according to the principles of the present invention comprises an item of surgical hardware that is made from a high strength metal, for example stainless steel or titanium, and which has a silver coating. The silver coating may be either silver plating, or a coating of silver salt. Generally the method of closing wounds according to the present invention comprises closing the wounds with surgical hardware made from a high strength metal and which has a silver coating.

The hardware of the present invention provides all of the advantages of being constructed from a high strength metal, including high strength and compact size, and the additional benefit of bacteriostatic action which helps to reduce the risk of complications resulting from the use of the hardware. The compact design permitted by the present invention ensures that the hardware has sufficient strength to hold the wound closed, and a sufficiently compact size that it does not unduly disturb the wound site or interfere with healing. The cost of manufacturing hardware according the principles of the present invention is only of marginally higher than the cost manufacturing conventional hardware. The method of this invention provides a way to close wounds with reduced risk of infection and complications.

These and other features and advantages will be in part apparent and in part pointed out hereinafter.

BRIEF DESCRIPTION OF THE DRAWINGS

35 FIGURE 1 is a perspective view of an internal (soft tissue) staple constructed according to the principles of this invention;

WO 92/13491 PCT/US92/00209

3

FIGURE 2 is a perspective view of a skin staple constructed according to the principles of this invention;

FIGURE 3 is a perspective view of a fascia staple constructed according to the principles of this invention;

FIGURE 4 is a. perspective view of a vascular staple constructed according to the principles of this invention;

5

10

30

35

FIGURE 5 is a perspective view of a vascular clip constructed according to the principles of this invention;

FIGURE 6 is a perspective view of a wire suture constructed according to the principles of this invention; and

FIGURE 7 is a cross-sectional view of the wire suture, taken along the plane of line 7-7 in Figure 6.

Corresponding reference numerals indicate corresponding parts throughout the several views of the drawings.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

principles of the present invention are indicated generally as 20, 22, 24, and 26 in Figures 1 - 4. A surgical clip constructed according to the principles of the present invention is indicated generally as 28 in Figure 5. A wire suture constructed according to the principles of the present invention is indicated generally as 30 in Figure 6. Although the present invention is described with respect to staples, clips, and sutures, the invention is not so limited and relates to any item of surgical hardware of the type used to close wounds.

The staples 20 - 26, the clip 28, and the suture 30 are made from a high strength surgical metal such as a stainless steel or titanium. Because they are constructed of a high strength material, these items have superior strength, and more importantly they can be designed to be small and compact so that they do not unnecessarily disturb the wound or interfere with proper healing. However, unlike any prior art item of surgical hardware, the staples 20 - 26, the clip 28, and the wire suture 30 have a silver coating. This is best shown in Figure 7 where the suture is shown as

5

10

15

20

25

30

comprising high strength surgical metal 32 with a silver coating 34. The silver coating provides a bacteriostatic action that inhibits infection. Thus infection is less likely to propagate when the surgical hardware of the present invention is used, and thus there is a reduced risk from infection-related complications from the use of such hardware.

The silver coating may be silver plating applied by a hot dip or electro-deposition process, or some other method. Alternatively, the coating may be a silver salt applied to the exterior of the item of hardware, for example silver nitrate, or silver-zinc allantoinate.

The method of the present invention relates to an improved method of closing surgical wounds with reduced risk of infection. The method comprises the step of closing the wound with a staple, wire suture, clip or other item of surgical hardware made from a high strength metal that has a silver coating.

The bacteriostatic effect of the hardware of this invention was tested by introducing a silver coated staple according to the principles of this invention, a stainless steel staple, and titanium staple into two difference agar media: Trypticase Soy Sheep Agar and Mueller Hinton Agar. Each of the staples was screened against staph aureus, Escherichia coli, Pseudomonas aeriginosa, and strep The plates were inoculated with a standard faecales. turbidity of a 0.5 McFarland standard. The staples were placed on top of the agar and the plates were incubated at 35°C for 24 hours. As illustrated in the following table, only the silver coated staple of the present invention showed any bacteriostatic action showing a zone of inhibition around the staple.

35		Stapha	ureus	Esche Co	richia li	Pseudo Aerigi		Str Faec	- <u>*</u>
40	Silver Plated	TSS Agar 11mm	M-H Agar 11mm	TSS Agar 6mm	M-H Agar	TSS Agar 22mm?	M-H Agar	TSS Agar	M-H Agar
40	Stainless Steel	•••	•••	•••	•••	•••	•••	•••	•••
	Titanium		•••	•••	• • •	•••	•••	• • •	

In view of the above, it will be seen that the several objects of the invention are achieved and other advantageous results attained.

As various changes could be made in the above constructions without departing from the scope of the invention, it is intended that all matter contained in the above description or shown in the accompanying drawings shall be interpreted as illustrative and not in a limited sense.

. 5

WHAT IS CLAIMED IS:


- 1. An improved staple, wire suture, clip, or other metallic item of surgical hardware of the type made from a high strength metal such as stainless steel or titanium, the improvement comprising a silver coating on the surface of the hardware.
- 2. The hardware according to claim I wherein the silver coating comprises silver plating.
 - 3. The hardware according to claim 1 wherein the silver coating comprises silver salts.
- 4. A staple, wire suture, clip, or other item of surgical hardware used to close a wound, made from a high strength metal to have a low profile design to minimize interference and disturbance of the wound, and having a bacteriostatic silver coating to reduce the risk of wound infection from the hardware.
 - 5. The hardware according to claim 4 wherein the silver coating comprises silver plating.
- 25 6. The hardware according to claim 4 wherein the silver coating comprises silver salts.
- 7. A method of closing surgical wounds with reduced risk of infection comprising the step of closing the wound with a staple, wire suture, clip or other item of surgical hardware made from a high strength metal that has a silver coating.
- 8. The method according to claim 4 wherein the silver coating comprises silver plating.
 - 9. The method according to claim 4 wherein the silver coating comprises silver salts.

- 10. A surgical staple having bacteriostatic coating.
- 11. A surgical staple according to claim 1 wherein said bacteriostatic coating is silver.

F/G.1.



F1G. 2.



F/G.3.




FIG. 4.







FIG. 7.







International Application No

		ECT MATTER (If several classification		
According	to International Paten	Classification (IPC) or to both Nation	al Classification and IPC	,
Int.Cl	. 5 A61B17/0	64		1
II. FIELDS	SEARCHED	Minimum Doc	rum estation Searched?	
Classificat	ion System		Classification Symbols	
-				
Int.Cl.	. 5	A61B		
			ber than Minimum Documentation nts are included in the Fields Searched ⁸	
III. DOCUM	MENTS CONSIDERE	D TO BE RELEVANT		
Category °		cument, II with indication, where appro	opriate, of the relevant passages 12	Relevant to Claim No.13
X		206 024 (BECTON) 30 D	ecember 1986	1-11
A	EP,A,O 2 see abst	255 248 (MINNESOTA) 3 cract	February 1988	3,6,9
A	CH,A,654	738 (BLÄTTLER) 14 M	arch 1986	
A	WO,A,8 1	02 668 (BURFORD) 1 0	ctober 1981	
A		28 421 (CULUMBIA) 16	_	
A	• •	46 715 (USSC) 3 March		
A	EP,A,O 4	06 014 (ETHICON) 2 Ja	anuary 1991	
		•		
"A" docu consi "E" earlic	idered to be of particul er document but publis	rai state of the art which is not	"T" later document published after the internal or priority date and not in conflict with the cited to understand the principle or theory invention "X" document of particular relevance; the claim	e application but underlying the ned invention
"L" docu which citati	is cited to establish the on or other special reas		cannot be considered novel or cannot be co involve an inventive step "Y" document of particular relevance; the claim cannot be considered to involve an inventive	ned invention we step when the
other	means	al disclosure, use, exhibition or the international filing date but dained	document is combined with one or more of ments, such combination being obvious to in the art. "&" document member of the same patent fami	a person skilled
IV. CERTIFI				
	ctual Completion of the	International Search	Date of Mailing of this International Searce	h Report
		RIL 1992	6. 05. 92	2
international S	Searching Authority EUROPEAN	N PATENT OFFICE	Signature of Authorized Officer BARTON S.	Zen.

International Application No

		ECT MATTER (If several classification s		
	to International Patent . 5 A61B17/0	Classification (IPC) or to both National C 64	Jassification and IPC	
II. FIELD	S SEARCHED			
		Minimum Docum	estation Searched?	
Classifica	tion System		Classification Symbols	
Int.C1	. 5	A61B		
		Documentation Searched other to the Extent that such Documents:		
III. DOCU		D TO BE RELEVANT ⁹		
Category °	Citation of Do	coment, ¹¹ with indication, where appropri	ate, of the relevant passages 12	Relevant to Claim No.13
X	EP,A,0 2 see cla	206 024 (BECTON) 30 Dec	ember 1986	1-11
A	EP,A,O 2 see abst	255 248 (MINNESOTA) 3 F cract	ebruary 1988	3,6,9
A	CH,A,654	738 (BLÄTTLER) 14 Mar	ch 1986	
A	WO,A,8 1	.02 668 (BURFORD) 1 Oct	ober 1981	
A	EP,A,0 3	28 421 (CULUMBIA) 16 A	ugust 1989	
A	EP,A,0 0	46 715 (USSC) 3 March	1982	
A	EP,A,0 4	06 014 (ETHICON) 2 Jan	uary 1991 	
"A" doc coe "E" earl filin "L" doc white cital "O" doc othe "P" doc late	usidered to be of particular document but publis ng date unment which may throw the is cited to establish to tion or other special reaument referring to an orer means unment published prior to than the priority date	eral state of the art which is not an relevance the international doubts on priority claims(s) or the publication date of another son (as specified) ral disclosure, use, exhibition or the international filing date but	"I" later document published after the it or priority date and not in conflict we cited to understand the principle or invention "X" document of particular relevance; the cannot be considered novel or cannot involve an inventive step "Y" document of particular relevance; the cannot be considered to involve an it document is combined with one or ments, such combination being obviding the art. "A" document member of the same pater.	ith the application but theory underlying the e claimed invention k be considered to e claimed invention nventive step when the tore other such docu- but to a person skilled
IV. CERTIF			The state of the s	Sausah Banari
Date of the	Actual Completion of the 27 API	e International Search RIL 1992	Date of Mailing of this International 6, 05, 92	Search Amport
International	Searching Authority EUROPEAN	N PATENT OFFICE	Signature of Authorized Officer BARTON S.	Ra

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO. US

9200209 56283

This annex sists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 27/04/92

Publication date		Patent family member(s)	Publicat date
30-12-86	US-A- AU-A-	4886505 3155089	12-12-89 29-06-89
	AU-B-	588598	21-09-89
			11-12-86
	JP-B- JP-A-	2005089 62002 947	31-01-90 08-01 - 87
	US-A-	4728323	01-03-88
	AU-B-	595333	29-03-90
			28-01-88
			29-01-91
	JP-A- 	63035260	15-02-88
14-03-86	None		
01-10-81	EP-A.B	0048246	31-03-82
4. 4. 4.	EP-A,B	0048247	31-03-82
	WO-A-		01-10-81
			07-10-81
			14-10-81
			16-10-84 07-10-86
16 00 00			28-05-91
10-08-83			17-08-89
			22-01-90
	AU-A-	7922991	03-10-91
03-03-82	AT-T-	7848	15-06-84
			04-03-82
			10-07-84
			21-02-85
			06-01-83 04-03-82
	WU-A- US-A-	4407286	04-03-82
02-01-91	 AU-A-	5788390	03-01-91
32 32 3	CA-A-	2020075	31-12-90
	JP-A-	3066378	22-03-91
	03-02-88 14-03-86 01-10-81 16-08-89	AU-A- AU-B- AU-A- JP-B- JP-A- O3-02-88 US-A- AU-B- AU-A- CA-A- JP-A- 14-03-86 None O1-10-81 EP-A, B EP-A, B WO-A- GB-A, B US-A- US-A- US-A- AU-A- JP-A- AU-A- JP-A- AU-A- DE-C- GB-A, B WO-A- US-A- US-A- O2-01-91 AU-A-	AU-A- 3155089 AU-B- 588598 AU-A- 5841786 JP-B- 2005089 JP-A- 62002947 03-02-88 US-A- 4728323 AU-B- 595333 AU-A- 7427987 CA-A- 1279573 JP-A- 63035260 14-03-86 None 01-10-81 EP-A,B 0048246 EP-A,B 0048247 W0-A- 8102667 GB-A,B 2072514 GB-A,B 2073024 US-A- 4476590 US-A- 4615705 16-08-89 US-A- 5019096 AU-A- 2989589 JP-A- 2017071 AU-A- 7922991 03-03-82 AT-T- 7848 AU-A- 7101681 CA-A- 1170536 DE-C- 3152256 GB-A,B 2100821 W0-A- 8200582 US-A- 4407286